

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6:		(1	1) International Publication Number:	WO 99/04445			
H01M 8/10, 8/02, C08J 3/02, 3/09	A1	(4	3) International Publication Date:	28 January 1999 (28.01.99)			
(21) International Application Number: PCT/US98/10464 (22) International Filing Date: 18 May 1998 (18.05.98)			(81) Designated States: AU, BR, CA, CN, JP, KR, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).				
(30) Priority Data: 08/895,059 16 July 1997 (16.07.97)	1	US	Published With international search rep	ort.			
(71) Applicant: HOECHST AKTIENGESELLSCHAFT D-65926 Frankfurt am Main (DE).	(DE/DI	E];					
(72) Inventors: ONORATO, Frank, J.; 23 Dryden Terrace burg, NJ 08865 (US). SANSONE, Michael, J.; nell Avenue, Berkeley Heights, NJ 07927 (US). I Stuart, M.; 16 Lenape Trail, Chatham, NJ 079 MARIKAR, Faruq; 2059 Algonquin Drive, Wes 07090 (US).	73 C FRENC 928 (U	or- CH, S).					
(74) Agents: GENOVA, John, M. et al.; Hoechst Celanes ration, Patent Dept., 86 Morris Avenue, Summit, (US).							
(54) Title: PROCESS FOR PRODUCING POLYBENZII	MIDAZ	7OI.	F PASTES AND GELS FOR USE IN	FUEL CELLS			
(57) Abstract	*****		MARKAN AND TO THE STATE OF THE	. • • • • • • • • • • • • • • • • • • •			
A method for producing polybenzimidazole (PBI) part of an acid, which permits the polymer to dissolve and form	ste or g m a ma	el u trix	seful in a fuel cell, mixing PBI polymer having a gel-like or paste-like consiste	powder with a suitable amount ency at room temperature.			
·							
			·				

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

l.	Albania	RS	Spain	LS	Lesotho	ST	Slovenia
AM	Armenia	FI	Finland	LT	Lithmania	SK	Slovakia
AΤ	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GB	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE.	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	1B	Ireland	MIN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malewi	US	United States of America
CA	Canada	tT.	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KB	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KĢ	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ.	New Zealand		
CM	Cameroon		Republic of Korea	PL.	Poland		
CN	China	KR	Republic of Kores	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	ıc	Saint Lucia	RU	Russian Federation		
DE	Germany	u	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SB	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PROCESS FOR PRODUCING POLYBENZIMIDAZOLE PASTES AND GELS FOR USE IN FUEL CELLS

5

Field of the Invention

This invention relates to the manufacture of a paste or gel for use as a polymer electrolyte in fuel cell applications.

10

15

20

25

30

Background of the Invention

Fuel cells can be configured in numerous ways with a variety of electrolytes, fuels and operating temperatures. For example, fuels such as hydrogen or methanol can be provided directly to the fuel cell electrode. Alternatively, fuels, such as methane or methanol, can be converted to a hydrogen rich gas mixture external to the cell itself and subsequently provided to the fuel cell. Air is the source of oxygen in most fuel cells, although in some applications, the oxygen is obtained by hydrogen peroxide decomposition or from a cryogenic storage system.

Although there are theoretically a limitless number of combinations of electrolyte, fuel, oxidant, temperatures and so on, practical systems include solid polymer electrolyte systems using hydrogen or hydrazine as the fuel source and pure oxygen as the oxidant. Polybenzimidazole (PBI) which has been doped with a strong acid is an example of a suitable solid polymer for use in an electrolyte system.

It is known in the art to imbibe polybenzimidazole (PBI) dense films with a strong acid to make a proton conducting media. Particularly, United States Patent

No. 5,525,436, issued June 11, 1996, described a method of doping PBI film with a strong acid, such as phosphoric acid or sulfuric acid, such that a single phase system is formed, i.e., acid is dissolved in the polymer.

Even in view of the advances in the art, the performance, high cost and processability of suitable polymeric electrolyte materials remain important considerations in fuel cell construction with respect.

polymeric media for fuel cells. There remains a need in the art for new materials for use in fuel cells.

Summary of the Invention

10

25

30

In one aspect, the present invention provides a method of preparing a polymeric, preferably PBI, paste or gel for use as an electrolyte in fuel cells. In one embodiment, the method comprises soaking finely divided PBI polymer in a suitable amount of an acid solution which permits the polymer to dissolve and form a matrix having a gel-like or paste-like consistency at room temperature.

In another aspect, the present invention provides a PBI paste or gel, which contains between about 70 to about 99.9% by weight of imbibed acid, which paste or gel is useful in fuel cells. These pastes or gels are prepared by the methods described herein.

In still another aspect, the invention provides a polymeric fabric coated with a PBI paste or gel according to the invention.

In yet another aspect, the invention provides a fuel cell comprising a PBI paste or gel, or coated fabric, according to this invention.

In a further aspect, the present invention provides a polymeric film coated with a PBI paste or gel of the invention.

In a further aspect, the present invention provides a polymeric film coated with a PBI paste or gel of the invention with a second polymeric film forming a sandwich structure.

In still a further aspect, the present invention provides a method for preparing an electrode for use in fuel cells by steps which include coating the electrode with a paste or gel of the invention.

Other aspects and advantages of the present invention are described further in the following detailed description of the preferred embodiments thereof.

Detailed Description of the Invention

10

15

20

25

30

The present invention provides an improvement over the art in methods of preparing a polymeric paste or gel which contains acid and is useful as an electrolyte in fuel cells, particularly chlorine-resistant fuel cells, and in the preparation of adhesives. Also provided are the pastes or gels prepared by the method of the invention, as well as fabric and film coated thereby, and fuel cells containing the pastes or gels of the invention.

Generally, according to the process of the invention, a polymeric paste or gel is prepared by mixing or soaking a polymeric powder with a suitably large amount of an acid solution which causes the polymer to dissolve and form a matrix having a gel-like or paste-like consistency at room temperature. By "suitably large amount of acid" is meant between about

70% to about 99.9%, by weight, of the polymer-acid solution mixture which forms the paste or gel.

Preferably, the polymer is PBI. PBI is currently preferred because the inventors have found that the basic nature of the PBI polymer causes it to have an affinity for acids, which permits it to retain the acids under extreme conditions. However, one of skill in the art can readily determine other suitable polymers, and desirably, other basic polymers such as e.g., polyaniline and polypyrimidine which swell upon mixture with the acid solutions described herein and form a paste- or gel-like matrix of the invention.

10

15

These PBI polymers, as well as other polymers useful in the invention, are readily obtained by one of skill in the art. Similarly, other polymeric materials permit production of gel or paste-like matrix of the invention having variances in acid content within the ranges provided herein.

An acid solution useful for addition to the polymer may contain approximately 100% acid, or may 20 contain a suitable acid diluted by or dissolved in a suitable solvent. For example, the acid solution desirably contains between about 5 weight percent (wt %) to about 100 wt% of an acid and up to about 95 wt% solvent. In a currently preferred embodiment, the acid 25 solution contains about 85 wt% acid and 15 wt% water or Suitable acids may include, for example, acetic acid, formic acid, nitric acid, hydrochloric acid, phosphoric acid, sulfuric acid, trifluoroacetic 30 acid, triflic acid and mixtures of these acids or mixtures of these acids and phosphoric acid. Currently, the preferred acid is phosphoric acid. However, one of skill in the art may readily select any

other suitable acid. The present invention is not limited to the choice of suitable acid, provided that the acid swells the polymer, e.g., PBI, and permits the formation of a matrix.

Currently, the most preferred acid solution contains about 85% by weight phosphoric acid and 15% by weight water. However, as stated above, other suitable acid solution concentrations using other selected acids may be readily determined and selected by one of skill in the art.

5

10

15

20

25

30

The polymer and acid solution may be combined and mixed at room temperature. However, any temperature between the freezing point and boiling point of the acid may be used. Optionally, the mixture is heated to enable it to reach a gel-like or paste-like consistency more rapidly than at room temperature. Desirably, the mixture is heated to between about 50°C to about 200°C, and more preferably to between about 100° to about 150°C. Suitably, the heating step is performed for between about five minutes to about four hours, and more preferably for about one hour. Upon cooling, the paste or gel matrix of the invention forms.

Thus, the present invention provides a PBI paste or gel. The resulting PBI paste or gel is characterized by containing between 70 - 99.9% acid, and preferably about 99% acid, by weight. Such a paste or gel is characterized by higher acid loadings and improved electrochemical properties compared to other compositions of the prior art for the same use. For example, the PBI paste or gel of this invention may be characterized by better retention of the acid than the pastes or gels of the prior art (e.g. phosphoric acid and silicon carbide pastes).

The PBI paste or gel of the invention is useful for a variety of purposes, and particularly in coating such materials as fabrics and films. The coated fabrics, and films, as well as the paste or gel, are useful in fuel cells. Desirably, where the paste or gel of the invention is used in fuel cells, it is produced by mixing the polymer and acid, as described above.

Thus, as another aspect, the present invention 10 provides a fabric or film coated with a PBI paste or gel of the invention. Suitable fabrics and films are desirably polymeric. Desirably, the fabric or film is derived from polymers including, but not limited to, polybenzimidazole (PBI) and derivatives thereof, 15 poly(pyridine), poly(pyrimidine), polyimidazoles, polybenzthiazoles, polybenzoxazoles, polyoxadiazoles, polyquinoxalines, polythiadiazoles, and poly(tetrazapyrenes). The presently preferred, and exemplified polymer, is PBI. Once the selected fabric 20 or film is coated according to the invention, it is particularly well suited for use in a fuel cell. These coated fabrics and films may be produced using methods well known to those of skill in the art.

Desirably, the selected polymeric fabric or film
is provided with a coating of between 0.1 to 50 µM of
the paste or gel. The coating is applied using
conventional means, such as roll coating, knife
coating, Gravure coating, brush coating, spray coating,
dip coating and other known techniques. General
descriptions of these types of coating methods may be
found in texts, such as Modern Coating and Drying
Techniques, (E. Cohen and E. Gutoff, eds: VCH
Publishers) New York (1992) and Web Processing and

Converting Technology and Equipment, (D. Satas, ed; Van Nostrand Reinhold) New York (1984). The manner of coating the fabric or film is not a limitation of this invention.

5

15

20

25

30

Alternatively, in one particularly desired embodiment, a fabric of the invention is imbibed with acid according to the method described in the copending, co-filed US patent application for "Process for Producing Polybenzimidazole Fabrics for Use in Fuel 10 Cells", which is incorporated by reference. Briefly, acid-imbibed fabric disclosed in that application contains between about 40 to about 95% acid, by weight, and more preferably about 50 to about 75% acid, by weight, of the imbibed fabric. A fabric containing polymeric fiber is utilized to prepare the acid-imbibed fabric. Examples of such polymers include, but are not limited to, polybenzimidazole (PBI), poly(pyridine), poly(pyrimidine), polyimidazoles, polybenzthiazoles, polybenzoxazoles, polyoxadiazoles, polyquinoxalines, polythiadiazoles, poly(tetrazapyrenes), and mixtures of sulfonated, non-sulfonated PBI and/or such polymeric fibers. Currently, the preferred fiber is a PBI fiber, which may be either sulfonated or non-sulfonated. Suitable fabrics are readily available from a variety of commercial sources, and are preferably woven and contain voids between the individual fibers in the fabric. However, knitted or non-woven fabrics which contain voids which permit imbibition of the acid, as described herein, may also be utilized. The fabric is imbibed with acid by soaking it in an appropriate acid solution, optionally in the presence of heat. A more detailed description of the acid-imbibed fabric and its

production are provided in the above-reference patent application.

In a further aspect, the present invention provides a polymeric film coated with a PBI paste or gel of the invention as described above, and joined or place adjacent to a second polymeric film, thereby forming a sandwich structure.

The coated fabric or film of the invention, including the "film sandwich" described above, is useful, for example, as the polymer electrolyte in a fuel cell of the invention. Thus, in another embodiment, the invention provides a method of preparing an electrode for use in a fuel cell by coating an electrode with a PBI paste and gel of the invention as described above. Another advantage of this invention is that the PBI paste or gel of the invention is more readily applied to the electrode material than are prior art electrolytes. The invention further provides fuel cells containing the electrodes, fabrics, and films coated with the PBI paste or gel according to the invention.

The following examples illustrate the preferred compositions and methods of the invention, using PBI as the exemplified polymer. These examples are illustrative only and do not limit the scope of the invention.

Example 1

10

15

20

25

30

An exemplary PBI paste of this invention is prepared as follows. Commercially available PBI polymer (lg) was added to a solution containing 117 g $85\%~H_3PO_4$ and 15%, by weight, water in a slow mixer. The mixture is agitated at a temperature of $100-150^{\circ}C$

to remove residual water until a consistent paste is obtained. The resulting paste or gel contains about 99% acid by weight.

5 Example 2

Another exemplary PBI paste is prepared as follows. PBI polymer (5g) was added to a solution containing 112 g 85% HPO₄ and 15%, by weight, water in a slow mixer. The mixture is agitated at a temperature of 100-150°C to remove residual water until a consistent paste is obtained. The resulting paste or gel contains about 96% acid by weight.

Example 3

PBI gel prepared from Example 1 was slot-coated at room temperature onto a phosphoric acid imbibed PBI fabric. The thickness of the coating was about 25 μm.

A similar coating was applied to a platinum electrode. A membrane electrode assembly was assembled from these materials and a second electrode such that the layers were ordered electrode/gel/fabric/gel/electrode.

Example 4

25

30

The membrane electrode assembly fashioned in Example 3 was then placed in a fuel cell. Under typical operating conditions at 0.7 volts the resulting current density and power density is approximately 450 milliamperes/cm 2 and 315 milliwatts/cm 2 , respectively.

Numerous modifications and variations of the present invention are included in the above-identified specification and are expected to be obvious to one of skill in the art. Such modifications and alterations to the compositions and processes of the present

invention are believed to be encompassed in the scope of the claims appended hereto.

WHAT IS CLAIMED IS:

1. A method for producing a polybenzimidazole (PBI) paste or gel comprising mixing a polymeric PBI powder with a suitable amount of an acid solution, which permits the polymer to dissolve and form a matrix having a gel-like or paste-like consistency at room temperature.

- The method according to claim 1 further comprising heating said mixture.
- 3. The method according to claim 1 wherein said acid solution comprises an acid and a solvent selected from the group consisting of water or methanol.
- 4. The method according to claim 3, wherein said acid is present in solution at between 5% by weight to about 100% by weight of said solution.
- 5. The method according to claim 4, wherein said solvent is present in said solution at between about 0 and about 5% by weight of said solution.
- 6. The method according to claim 1, wherein said acid is selected from the group consisting of phosphoric acid, acetic acid, formic acid, nitric acid, hydrochloric acid, sulfuric acid, methanesulfonic acid, trifluoroacetic acid, triflic acid and mixtures thereof.
- 7. The method according to claim 3, wherein the suitable amount of said acid solution is between about

70 to about 99.9% of the total weight of said paste or gel mixture.

- 8. The method according to claim 7, wherein the suitable amount of said solution is between about 95 to about 99% of the total weight of said paste or gel mixture.
- 9. The method according to claim 7, wherein the amount of said PBI in said paste or gel is between about 0.1% to about 30% by weight of said paste or gel mixture.
- 10. The method according to claim 2 wherein said mixture is heated to between about 50 to 200°C for a time sufficient for the mixture to form a paste or gel.
- 11. The method according to claim 10 wherein said time is between 5 minutes to 4 hours.
- 12. A PBI paste or gel comprising a phosphoric acid solution content of between about 70 to 99.9% by weight and about 0.01 to about 30% by weight, PBI, of the total weight of said paste or gel.
- 13. A PBI paste or gel produced according to claims 1-11.
- 14. A fuel cell comprising a paste or gel, which comprises a phosphoric acid solution content of between about 70 to 99.9% by weight and about 0.01 to about 30% by weight, PBI, of the total weight of said paste or gel.

15. A polymeric fabric or film coated with a paste or gel, which comprises a phosphoric acid solution content of between about 70 to 99.9% by weight and about 0.01 to about 30% by weight, PBI, of the total weight of said paste or gel.

- 16. The fabric according to claim 15, which has been imbibed with acid prior to coating with said paste or gel.
- 17. A fuel cell comprising a fabric coated with a paste or gel, which comprises a phosphoric acid solution content of between about 70 to 99.9% by weight and about 0.01 to about 30% by weight, PBI, of the total weight of said paste or gel.
- 18. A polymeric film coated with a paste or gel, which comprises a phosphoric acid solution content of between about 70 to 99.9% by weight and about 0.01 to about 30% by weight, PBI, of the total weight of said paste or gel.
- 19. A method of preparing an electrode for use in fuel cells comprising coating said electrode with a paste or gel which comprises a phosphoric acid solution content of between about 70 to 99.9% by weight and about 0.01 to about 30% by weight, PBI, of the total weight of said paste or gel.

INTERNATIONAL SEARCH REPORT


Inte onal Application No PCT/US 98/10464

A CLASSI	FICATION OF SUBJECT MATTER			101700 30		
IPC 6	H01M8/10 H01M8/02 C	08J3/02	C08J3/0	9		
According to	International Patent Classification (IPC) or to both natk	onal dassification e	and IPC			
	SEARCHED					
Minimum do	cumentation searched (classification system followed t H01M C08J	y classification syn	nbols)			
Documentat	tion searched other than minimum documentation to the	autoat that numb de		d. Ale the state of		
Documents.	to the particular than the particular to the	extent mat such of	ocuments are inclu	ided in the fields se	arched	
					e e	
Electronic d	ata base consulted during the international search (nam	ne of data base an	d. where practical,	search terms used)	
	ENTS CONSIDERED TO BE RELEVANT					
Category *	Chation of document, with indication, where appropria	te, of the relevant	passages		Relevant to claim No.	
P,X	NO OR DADOR & (MOTOROLA TE	1 14 15				
٠,^	WO 98 04008 A (MOTOROLA IN 29 January 1998	L)			1-14,19	
	see claims 1-4,11			•		
	see page 5, line 12 - page	7, line 7	7			
P,X	see page 7, line 36 - page -& US 5 693 434 A (CHANGMI	NG FT AL)	+		1-14,19	
. ,	2 December 1997	-			1 14,13	
	see column 3, line 66 - co	1umn 5, 11	ine 18;			
	claims 1,5 see column 5, line 53 - li	ne 59				
Α	WO 97 23919 A (HOECHST AG				14	
	(DE); CLAUSS JOACHIM (DE); 3 July 1997	DECKERS (areu j			
	see page 6, line 24 - line	25				
	see page 11, paragraph 1					
		-/	_			
		·				
			*			
X Funt	ner documents are listed in the continuation of box C.	ĺχ	Patent family r	nembers are listed	in annex.	
* Special cat	tegories of cited documents :					
"A" docume	int defining the general state of the art which is not		or priority date and	Inot in conflict with	rnational filing date the application but	
conside	ered to be of particular relevance locument but published on or after the international		invention		eary underlying the	
nu A o	ate nt which may throw doubts on priority claim(s) or		cannot be conside	far relevance; the cred novel or canno	t be considered to	
wnich	is cited to establish the publication date of another to or other special reason (as specified)	~~° d	locument of partica	dar relevance; the	Cument is taken alone Calmed Invention	
	int referring to an oral disclosure, use, exhibition or		document is comb	ined with one or m	ventive step when the ore other such docu-	
"P" docume	mit published prior to the international filing date but an the priority date claimed		in the art.	-	us to a person skilled	
	actual completion of their mational search			of the same patent he international sea		
		'	or maining Of t		мы пород	
19	5 September 1998		25/09/1	998 -		
Name and m	nailing address of the ISA		Authorized officer			
	European Patent Office, P.B. 5818 Patentiaan 2 NL + 2280 HV Rijswijk					
	Tel. (+31-70) 340-2040, Tx. 31 651 epo nt, Fax: (+31-70) 340-3016		D'hondt, J			
orm PCT/ISA/2	10 (second sheet) (July 1992)					

INTERNATIONAL SEARCH REPORT

Inte onal Application No PCT/US 98/10464

Continu	ntion) DOCUMENTS CONSIDERED TO BE RELEVANT	PCT/US 98/10464
ategory .	Citation of document, with indication, where appropriate, of the relevant passages	Delminat to stalm No.
		Relevant to claim No.
	WO 96 13872 A (UNIV CASE WESTERN RESERVE) 9 May 1996 see page 13, paragraph 1 - paragraph 2; claims 1-3,7	14
4	US 5 599 639 A (SANSONE MICHAEL J ET AL) 4 February 1997 see claim 1; example 10	14
1	WO 92 10527 A (DOW CHEMICAL CO) 25 June 1992 see page 8, last paragraph - page 9, paragraph 1	6
A	US 4 945 156 A (JENEKHE SAMSON A ET AL) 31 July 1990 see column 5, line 3 - line 10 see column 1, last paragraph - column 2, line 1	6
P,A	S. K. ZECEVIC ET AL: "Kinetics of 02 Reduction on a Pt Electrode Covered with a Thin Film of Solid Polymer Electrolyte" JOURNAL OF THE ELECTROCHEMICAL SOCIETY, vol. 144, no. 9, - 9 September 1997 pages 2973-2982, XP002077420 MANCHESTER, NEW HAMPSHIRE US see abstract see page 2973, left-hand column, paragraph 1 see page 2974, left-hand column, line 12 - line 17	6,19
A	W.WIECZOREK ET AL: "PROTONIC HYDROGELS FOR APPLICATION IN AMBIENT TEMPERATURE FUEL CELLS" NEW MATER. FUEL CELL SYST. I, PROC. INT. SYMP., 1ST MONTREAL CANADA JULY 9-13 1995, - 1995 XP002077419 see page 116, paragraph 2 see abstract	14
A	US 5 525 436 A (SAVINELL ROBERT F ET AL) 11 June 1996 cited in the application	



information on patent family members

Inte Yonal Application No PCT/US 98/10464

Patent document cited in search repor	t	Publication - date		atent family nember(s)	Publication date
WO 9804008	Α	29-01-1998	US	5693434 A	02-12-1997
WO 9723919	Α	03-07-1997	DE	19548421 A	11-09-1997
WO 9613872	A	09-05-1996	US	5525436 A	11-06-1996
			UA	4017595 A	23-05-1996
			EP	0787369 A	06-08-1997
US 5599639	Α	04-02-1997	JP	9073908 A	18-03-1997
WO 9210527	Α	25-06-1992	US	5196259 A	23-03-1993
			CA	2097296 A	08-06-1992
			CA	2097710 A	08-06-1992
			EP	0560897 A	22-09-1993
			EP	0560922 A	22-09-1993
	•		EP	0560923 A	22-09-1993
			JP	6503597 T	21-04-1994
			JP	6503521 T	21-04-1994
			JP	6503598 T	21-04-1994
			WO	9210536 A	25-06-1992
			WO	9210364 A	25-06-1992
US 4945156	Α.	31-07-1990	NONE		
US 5525436	Α	11-06-1996	. AU	4017595 A	23-05-1996
			EP	0787369 A	06-08-1997
			WO	9613872 A	09-05-1996